



## EXPECTED DURABILITY AND WARRANTY OF CAR WRAPPING FILMS

Car wrapping film installers often communicate imprecise information about the expected durability and warranty period of the film installed. In order to provide detailed and precise data, we have collected the real time periods provided by certain manufacturers.

It is important to know that the expected durability of car wrapping films installed vertically differs considerably from the durability related to horizontal application. The information below describes in most cases both types of application, with reference to certain brands and specific films.

### Expected durability of AVERY DENNISON SUPREME WRAPPING FILMS under Central European weather conditions

	Expected durability (vertical application)	Expected durability (horizontal application)
<b>Black and white</b>	12 years	6 years
<b>Colours</b>	10 years	5 years
<b>Metallic and pearlescent</b>	5 years	2.5 years
<b>Brushed and carbon</b>	4 years	1 year

Expected durability (vertical application)	
<b>Conform Chrome Silver</b>	3 years
<b>Conform Chrome other colours</b>	2 years

	Expected durability (vertical application, 0-10°)	Expected durability (non-vertical application, 10-45°)	Expected durability (horizontal application)
<b>Diamond</b>	3 years	1 year	1 year

Wraptrade.com Edition	Expected durability (vertical application)	Warranty, vertical (horizontal) application
<b>Silky Maya Blue</b>	3 years	1,5 (0,5) years
<b>Silky Charcoal</b>	3 years	1,5 (0,5) years
<b>Silky Bronze</b>	3 years	1,5 (0,5) years
<b>Silky Black</b>	3 years	1,5 (0,5) years
<b>Silky Orion Black</b>	3 years	1,5 (0,5) years
<b>Nardo Grey</b>	10 years	5 years

<b>Brilliant GT Yellow</b>	10 years	5 years
<b>Brilliant Miami Blue</b>	10 years	5 years
<b>Brilliant Toxic Green</b>	10 years	5 years
<b>Frozen Bronze</b>	7 years	3 (1) years
<b>Blunt Military Green</b>	10 years	2 years
<b>Laurel Green</b>	10 years	5 years
<b>Tiffany</b>	10 years	5 years

	Expected durability (vertical application, 0-10°)	Expected durability (non-vertical application, 10-45°)	Expected durability (horizontal application)
<b>ColorFlow</b>	4 years	1 year	1 year

The actual performance depends on factors including the preparation of the surface, weather conditions and the maintenance of the film. The durability of the film is reduced by Southern orientation, long-term high temperatures (e.g. Southern Europe), industrial contamination and high altitudes. The warranty does not cover the reduction of gloss, only the replacement (or, if not possible, the refund) of the defected material

### Warranty periods for MACTAC COLOURWRAP car wrapping films are identical to their expected durability values under Central European weather conditions.

It is important to note in connection with warranty that it does not cover visible defects not related to natural impacts.

	Expected durability and warranty, vertical application	Expected durability and warranty, horizontal application
<b>Black and white</b>	8 years	5 years
<b>Colours</b>	6 years	3 years
<b>Metallic</b>	4 years	2 years

### Warranty periods for INOZETEK car wrapping films are identical to their expected durability values under Central European weather conditions.

It is important to note in connection with warranty that it does not cover visible defects not related to natural impacts.

	Expected durability and warranty, vertical application	Expected durability and warranty, horizontal application
<b>Colours</b>	6 years	2 years
<b>Metallic</b>	4 years	2 years
<b>Pearlescent</b>	4 years	2 years

The manufacturer does not provide warranty for the ORACAL car wrapping range, however they offer expected durability data that are valid with Central European climatic conditions and professional application.

	Expected durability and warranty, vertical application, under central european weather conditions
<b>Black and white</b>	12 years
<b>Colours</b>	10 years
<b>Metallic</b>	5 years
<b>Copper, Orient brown metallic, Bronze, Pyrite, Graphite metallic, Red gold L metallic &amp; Nacre</b>	3 years

Warranty periods for IRISTEK car wrapping films are identical to their expected durability values under Central European weather conditions.

It is important to note in connection with warranty that it does not cover visible defects not related to natural impacts.

	Expected durability and warranty, vertical application, under central european weather conditions
<b>Colours</b>	3 years
<b>Metallic</b>	3 years
<b>Pearl</b>	3 years
<b>Matt</b>	3 years

